

#### PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

\* Low sheen finish prevents dazzling reflected sunlight off decks

\* Easy application

\* Available in a range of colours

The tough polyurethane resin protects decks against everyday wear and tear.

#### PRODUCT INFORMATION

|                           |   |
|---------------------------|---|
| <b>Colour</b>             | YJB000-White, YJB339-Pale Blue, YJB923-Squall Blue, YJC089-Cream, YJF684-Grey, YJG090-Beige |
| <b>Finish</b>             | Low sheen   |
| <b>Specific Gravity</b>   | 1.4   |
| <b>Volume Solids</b>      | 54%   |
| <b>Typical Shelf Life</b> | 2 yrs   |
| <b>VOC (As Supplied)</b>  | 357 g/lt  |
| <b>Unit Size</b>          | 750 ml  |

#### DRYING/OVERCOATING INFORMATION

|                 | Drying |  |       |  |       |  |       |  |
|-----------------|--------|--|-------|--|-------|--|-------|--|
|                 | 5°C    |  | 15°C  |  | 23°C  |  | 35°C  |  |
| Touch Dry [ISO] | 5hrs   |  | 4hrs  |  | 3hrs  |  | 2hrs  |  |
| Dry To Walk On  | 4days  |  | 3days |  | 2days |  | 1days |  |

  

|               | Overcoating           |       |       |       |       |       |       |       |
|---------------|-----------------------|-------|-------|-------|-------|-------|-------|-------|
|               | Substrate Temperature |       |       |       |       |       |       |       |
|               | 5°C                   |       | 15°C  |       | 23°C  |       | 35°C  |       |
| Overcoated By | Min                   | Max   | Min   | Max   | Min   | Max   | Min   | Max   |
| Interdeck     | 24hrs                 | 4days | 20hrs | 3days | 16hrs | 2days | 12hrs | 1days |

#### APPLICATION AND USE

##### Preparation

##### PREVIOUSLY PAINTED SURFACES:

**In Good Condition:** Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

**In Poor Condition:** Remove all previous coatings and prime the substrate.

**PRIMING:** All preparation for bare substrates is covered on the appropriate primer datasheet.

**BARE WOOD:** Prime with Yacht Primer or UCP.

**STEEL:** Prime with Yacht Primer or Interprotect.

**ALUMINIUM:** Prime with Etch Primer followed by either Yacht Primer or Interprotect.

**GRP:** Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 180-220 grade paper. No priming necessary.

**AGED/WEATHERED GELCOATS:** Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with Perfection Undercoat prior to topcoat application.

**ALL SUBSTRATES:** If any filling is required use the appropriate product from the Interfill range.

|                                 |  |
|---------------------------------|--|
| <b>Method</b>                   | Sand the primer with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.  |
| <b>Hints</b>                    | <p><b>Mixing</b> Stir well before use.</p> <p><b>Thinner</b> YTA800 Thinners No.1</p> <p><b>Cleaner</b> YTA800 Thinners No.1</p> <p><b>Ventilation and Humidity Control</b> Apply in dry, well ventilated conditions.</p> <p><b>Other</b> For best results either stipple by brush or use a mohair roller.</p> |
| <b>Some Important Points</b>    | Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.   |
| <b>Compatibility/Substrates</b> | Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.   |
| <b>Number of Coats</b>          | 1-2  |
| <b>Coverage</b>                 | (Theoretical) - 9.50 (m <sup>2</sup> /lt)  |
| <b>Recommended DFT</b>          | 50 microns dry   |
| <b>Recommended WFT</b>          | 93 microns wet   |
| <b>Application Methods</b>      | Brush, Roller  |

#### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

|                |   |
|----------------|---|
| <b>Storage</b> | <p><b>GENERAL INFORMATION:</b><br/>Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b><br/>Interdeck should be kept in securely closed containers during transport and storage.</p>   |
| <b>Safety</b>  | <p><b>GENERAL:</b> Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Reminders of Interdeck cannot be disposed of through the municipal waste route or dumped without permit. Disposal of reminders must be arranged for in consultation with the authorities.</p> |



**IMP  
ORT  
ANT  
NOT  
ES**

*The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

Please refer to your local representative or visit [www.yachtpaint.com](http://www.yachtpaint.com) for further information.

✘<sup>®</sup>, International<sup>®</sup>, the AkzoNobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel. ©Akzo Nobel 2009.

Ref: 05000108  
Issue Date: 14-Dec-2007  
Supersedes: 1-Dec-2007