

PRODUCT DESCRIPTION

Perfection 2-part polyurethane is the ultimate performing, high gloss topside finish. It provides the longest-lasting, ultra-high gloss finish that has superb colour-retention, together with excellent chemical and abrasion resistance. It has been formulated specifically to enable skilled amateur users to achieve professional-quality results with ease. UV filters combined with the chemical cure of the polyurethane to give the longest life possible.

* Hardest, abrasion-resistant finish making it an excellent choice for use on high wear areas e.g. decks (with Intergrip additive).

* Chemically resistant to diesel, petrol, oil, mild acids and alkalis

PRODUCT INFORMATION

Colour	YHA183, YHA184, YHA192-Off White, YHA194-Oyster White, YHA198-Mat'horn White, YHA216-Royal Blue, YHB000-Snow White, YHB663-Jade Mist Green, YHE294, YHF991-Mauritius Blue, YHK990-Flag Blue, YHS056-Fight. Lady Yellow, YHS070-Cream, YHS299-Rochelle Red, YHS936, YHY999-Jet Black
Finish	High Gloss
Specific Gravity	1.167
Volume Solids	49.0%
Mix Ratio	2:1 by volume (as supplied) , Converter/Curing Agent - YGB001
Typical Shelf Life	2 yrs
VOC (As Supplied)	486 g/ltr
Unit Size	750 ml 2.5 Lt (some colours only)

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		10°C		23°C		35°C	
Touch Dry [ISO]	11hrs				4hrs		3hrs	
Pot Life	5hrs				2hrs		1hrs	

	Overcoating							
	Substrate Temperature							
	5°C		10°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Perfection	28hrs	4days	-	-	6hrs	2days	4hrs	1days

APPLICATION AND USE

Preparation

PREVIOUSLY PAINTED SURFACES:

In Good Condition: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

In Poor Condition: Remove all previous coatings and prime the substrate.

PRIMING: All preparation for bare substrates is covered on the appropriate primer datasheet.

BARE WOOD: Prime with UCP or Interprotect.

STEEL: Prime with Interprotect.

ALUMINIUM: Pre-prime using Etch Primer. Prime with Interprotect.

GRP: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Sweep blast or abrade with 180-220 grade paper. No priming necessary.

AGED/WEATHERED GELCOATS: Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce

gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with Perfection Undercoat prior to topcoat application.

ALL SUBSTRATES: Use Perfection Undercoat.

Method	Sand the undercoat smooth with 320-400 grade (grit) wet or dry paper. Remove dust with a tack rag. Apply 2-3 coats.
Hints	<p>Mixing Stir contents of each part prior to mixing. Add Curing Agent to the Base, stir and leave for 20 minutes to allow bubbles to disperse.</p> <p>Thinner International Retarder Thinner #9.</p> <p>Cleaner International Retarder Thinner #9.</p> <p>Ventilation and Humidity Control Apply in dry, well ventilated conditions. Avoid excessively humid conditions, over 80% relative humidity.</p> <p>Other Best applied at 15°C. For lighter colors, mix the first coat of finish 50:50 with the undercoat to improve the depth of color and opacity. Both products should be mixed with respective curing agents first. For best results when applying by roller, smooth off with a pad or brush. If using as a deck paint, mix in non-slip additive. Full hardness is achieved after 7-10 days at 15°C/59°F. If required, Perfection Matting Additive (YZM914) is available for use with Perfection. See Perfection Matting Additive datasheet for details on use.</p>
Some Important Points	Do not use unless mixed thoroughly with the curing agent at specified ratio. Avoid painting in direct sunlight. Avoid applying late in the evening as condensation can cause a loss of gloss during overnight cure. Allow to dry in a well ventilated environment. Product temperature should be minimum 15°C/59°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 30°C/86°F. Substrate temperature should be minimum 5°C/40°F and maximum 30°C/86°F.
Compatibility/Substrates	Do not use Perfection on flexible constructions. Will crack on carvel and clinker/lapstrake hulls. Perfection should not be used over any one-pack products. Not suitable for permanently immersed surfaces.
Number of Coats	2-3
Coverage	(Theoretical) - 13.30 (m ² /lt) (Practical) - 12.00 (m ² /lt)
Recommended DFT	37 microns dry
Recommended WFT	75 microns wet
Application Methods	Brush, Roller , DO NOT SPRAY

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of this product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Perfection should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Contains isocyanates which may be harmful to the respiratory tract. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.


Remainders of Perfection cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.



**IMP
ORT
ANT
NOT
ES**

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit www.yachtpaint.com for further information.

 International[®], the AkzoNobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel. ©Akzo Nobel 2009.

Ref: 05000442
Issue Date: 6-Dec-2009
Supersedes: 1-Dec-2009