

A Quality Product from Hawkeye Industries Inc.



Duratec® Polyester Base Primer

A low-porosity, high-building, fairing and shaping primer for composites, wood, MDF, GRP, foam, plaster and clay

Usage

For fairing and shaping composite plugs, patterns and models and a variety of other substrates. Used by manufacturers in the automotive, housing, leisure products, marine and transportation industries.

Features

You'll save time and labor and add quality with Duratec Polyester Base Primer.

Here's why you should choose Duratec Polyester Base Primer—

Easy to apply – apply with a sprayer, brush or roller.

Rapid coat buildup—builds quickly—between 1 to 3 mm,

40-120 mils, maximum wet-on-wet application with minimum sag on vertical surfaces.

Quick Shaping—quickly shaped by knife, file or sandpaper.

Fast air curing—saves time. The primer quickly air cures to an easily sandable surface, which provides a stable base for other coatings.

High heat distortion temperature—reduces the risk of post-cure or distortion from elevated temperature due to exotherm and consequential print-through of substrates.

Duratec Polyester Base Primer

707-051 Tan

(Link to MSDS)



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316
Tel 909-546-1160; Toll Free 800-977-0060; Fax: 909-546-1161
Email productinfo@duratec1.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.



Product No. 707-051 Tan

**Data Sheet
Continued**

Duratec Polyester Base Primer

Pg. 2

Product Properties

All time calculations are based on temperatures of 77°F, 25°C

Viscosity

*As measured on a Brookfield Viscometer
Model RVF, Spindle #2 at 20 rpm*

2200 cps

Thixotropic Index

5.8 - 6.0

Gel Time

*Sample based on a 100 g mass,
catalyzed at 2 percent with mekP*

15 min

Heat Distortion Temperature

<212°F, 100°C

Weight per Gallon

7.66 lb., 3.48 kg

Coverage per Gallon

20 mil thickness - 55-60 ft²
500 micron thickness - 4-5 m²

Link to Application Guide for Duratec Polyester Base Primer:

- [Sealing, Fairing, Priming and Surfacing Application: Plugs, Patterns and Models](#)

Duratec Polyester Base Primer is among the many fine Duratec products marketed worldwide by Hawkeye Industries Inc.

[📁 Contents/Literature CD](#) [📁 Trouble Shooting Guide](#)

Rev 9-14-05



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316
Tel 909-546-1160; Toll Free 800-977-0060; Fax: 909-546-1161
Email productinfo@duratec1.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.