

TRIDENT FOAMS LIMITED



✕TRIPOR ✕TRICAST ✕TANCAST ✕AUTOFROTH ✕AUTOPOR ✕MHD

TRICAST 2 POLYURETHANE FOAM

DESCRIPTION

Tricast 2 is a low density rigid polyurethane foam available in sheet form, and is suitable for a wide variety of building insulation and G.R.P. manufacturing processes. Tricast 2 does not contain any C.F.C.s., H.C.F.C.s or H.F.A.s.

DIMENSIONS:-

Thickness: 6 - 600mm
Width: 600, 1200mm
Length: 600, 1200, 2400mm.
Other sizes on request.

TECHNICAL PROPERTIES

Nominal density	32kg/m ³ (2lbs/ft ³)
Initial thermal conductivity	0.030 W/m °K @ 10°C
Closed Cell (BS.4370 Part.2 Method 10)	> 95%
Compressive Strength (BS.4370 Part.1 1968 Method 3)	
Normal to major plane	170 kPa
Parallel to major plane	100 kPa
Tensile Strength (BS.4370 Part.2 1973 Method 9)	
Parallel to major plane	230 kPa
Cross break strength (BS 4370 Part.1 method 4)	
Perpendicular to major plane	245 kPa
Shear Strength (BS.4370 Part.2 1973 Method 6)	
Parallel to major plane	-
Upper service temperature limit	70°C
Dimensional stability (BS 4370 Part.1 method 5A)	
70°C for 7 days	<+0.5%
50°C / 100%rh for 7days	<+0.5%
-20°C for 7 days	No change

APPLICATIONS

Building insulation, refrigeration doors & panels, GRP manufacture - tanks, cabinets, sections and shaping, withstanding the application of glass & resin at lamination stage.

Whilst the information above is true and accurate to the best of our knowledge and belief, all liability for errors and omissions, damage or loss resulting here from is hereby excluded. Recommendations for use should be verified as to suitability and compliance with actual requirements, specifications and any applicable laws and regulations.

BKB House, Goyt Valley Industrial Estate, Off Station Road, Furness Vale, High Peak, SK23 7SN.

Tel 44 (0) 1663 740120 Fax 44 (0) 1663 740121

Registered in England No.2026997 Directors: C.P.Kenyon MD, C.F.Kenyon

AU TOFROTH® is a registered trademark of the BASF Corporation (USA).